

DESCRIPTION

METHOD FOR TREATMENT OF SOLID PHARMACEUTICAL PREPARATION PRIOR
TO PRINTING AND SOLID PHARMACEUTICAL PREPARATION SUBJECTED TO
TREATMENT PRIOR TO PRINTING

5

Technical Field

The present invention relates to a method for treating a solid dosage form to improve the printability and abrasion resistance of a print to be produced on a surface of the solid dosage form, and a solid dosage form having improved abrasion resistance of a print or improved printability, which is afforded by the treatment.

Background Art

There are many kinds of tablets and capsules that resemble one another in the size, color tone and shape. To identify each preparation, a company name, a company mark, a product name, ingredient contents and the like are often coded and directly imprinted on the preparation. For imprinting, engraving and printing are available. While engraving is employed for plain tablets free of coating, a subset of film-coated tablets and the like, printing is employed for many film-coated tablets, sugar-coated tablets, capsules and the like.

For tablets and capsules, polishing with wax (in this specification, it means "wax" in a narrow sense, namely, fatty acid ester of higher alcohol; examples: carnauba wax, bees wax and the like) is often applied for the purpose of increasing the commercial value by glossy appearance, protecting a preparation from highly humid environment, preventing staining with coloring agents, improving slip property to facilitate handling in later operations of printing, inspection, packing and the like, and the like (e.g., Porter and two others, Pan Coating of Tablets and Granules, edited by Herbert A. Lieberman and one other, Pharmaceutical Dosage Forms Tablets, vol. 3, US,

further studies based on these findings and completed the present invention.

Accordingly, the present invention provides

- 5 [1] a treatment method for improving printability and/or abrasion resistance of a print to be produced on a surface of a solid dosage form, which comprises treating said surface with a polyethylene glycol-containing aqueous solution before printing,
- 10 [2] the method of the above-mentioned [1], wherein polyethylene glycol has an average molecular weight of not less than about 1,000,
- [3] the method of the above-mentioned [1], wherein polyethylene glycol has an average molecular weight of about 3,000 to about 9,000,
- 15 [4] the method of the above-mentioned [1], wherein the amount of polyethylene glycol to be added by the treatment is about 0.01% to about 1.0% in a weight ratio to the finished preparation,
- 20 [5] the method of the above-mentioned [1], wherein the solid dosage form is a film-coated tablet,
- 25 [6] a method for producing a solid dosage form with a printed surface, which comprises treating the surface of the solid dosage form with a polyethylene glycol-containing aqueous solution and then printing on said surface,
- 30 [7] the method of the above-mentioned [6], wherein polyethylene glycol has an average molecular weight of not less than about 1,000,

[8] the method of the above-mentioned [6], wherein polyethylene glycol has an average molecular weight of about 3,000 to about 9,000,

5 [9] the method of the above-mentioned [6], wherein the amount of polyethylene glycol to be added by the treatment is about 0.01% to about 1.0% in a weight ratio to the finished preparation,

10 [10] the method of the above-mentioned [6], wherein the solid dosage form is a film-coated tablet,

[11] a solid dosage form treated by the method of any of the above-mentioned [1] to [5],

15

[12] a solid dosage form with a printed surface, which can be obtained by any of the above-mentioned [6] to [10],

[13] a solid dosage form which has a coating film comprising
20 polyethylene glycol but free of bees wax and carnauba wax on its surface, and is printed on the surface of the coating film, and

[14] a solid dosage form which has a coating comprising
25 polyethylene glycol but free of bees wax and carnauba wax on its surface, and is printed on the surface of the coating.

Detailed Description of the Invention

The present invention provides a method for treating a
30 solid dosage form to improve the abrasion resistance of a print to be produced on a surface of the solid dosage form. As used herein, by "to improve the abrasion resistance of a print" is meant, for example, significantly reducing the degree of abrasion of the print produced on the solid dosage form as

compared to a case free of such treatment, in the print abrasion test to be described in detail in the Examples to be mentioned below.

The solid dosage form applicable to the treatment method
5 of the present invention is not particularly limited in the dosage form as long as its surface can be printed on and, for example, tablet, capsule, troche, pill, suppository and the like can be mentioned. In view of the necessity of imprinting by printing, the method is particularly preferably applied to
10 tablets and capsules.

In this specification, the "solid dosage form" means not only pharmaceutical products but also any composition processed to have a certain dosage form of animal drug, agricultural chemical, fertilizer, sanitary products and the like.

15 The active ingredient to be contained in the solid dosage form is not particularly limited. For example, substances effective for the prophylaxis or treatment of various diseases, which are exemplified by, but not limited to, substances having sleep-inducing action, tranquilizer activity,
20 antibiotic activity, hypotensive action, antianginal activity, analgesic activity, anti-inflammatory activity, mental stabilizing action, diabetes treatment activity, diuretic action, anticholine activity, antihyperacidic action, antiepileptic action, ACE inhibitory activity, β -receptor
25 antagonistic or agonistic activity, anesthetic action, anorexigenic action, antiarrhythmic action, antidepressive action, anticoagulant activity, anti diarrheal action, antihistaminic activity, antimalarial action, antitumor activity, immunosuppressive activity, anti-Parkinson's syndrome
30 action, antipsychotic action, antiplatelet activity, antihyperlipidemic action and the like, and the like, substance having detergent action, substances having flavoring, fertilizer, and deodorizing actions, animal/pest exterminating substances, substances having insecticidal action, substances

having herbicidal action, plant growth regulators and the like.

Where necessary, the solid dosage form of the present invention can contain a carrier acceptable for the use of the solid dosage form, together with the active ingredient. In the
5 case of a pharmaceutical preparation, for example, it can contain a pharmaceutically acceptable carrier. As the pharmaceutically acceptable carrier, various organic or inorganic carriers conventionally used as preparation materials are used and, for example, excipient, lubricant, binder,
10 disintegrant, thickener and the like are appropriately added in suitable amounts. Where necessary, additives such as preservative, antioxidant, coloring agent, sweetening agent and the like can also be used.

Examples of the excipient include, but are not limited
15 to, lactose, sucrose, glucose, maltose, corn starch, flour starch, mannitol, xylitol, sorbitol, maltitol, erythritol, lactitol, palatinit, crystalline cellulose, light anhydrous silicic acid, dextrin, carboxymethylstarch, gelatin, synthesis aluminum silicate, magnesium alumino metesilicate, magnesium
20 oxide, calcium phosphate, calcium carbonate, calcium sulfate and the like.

Examples of the lubricant include, but are not limited to, stearic acid, magnesium stearate, calcium stearate, talc,
waxes, DL-leucine, sodium lauryl sulfate, magnesium lauryl
25 sulfate, polyethylene glycol, aerosil (usable as antistatic agent) and the like.

Examples of the binder include, but are not limited to, gelatin, pullulan, hydroxypropylmethylcellulose (HPMC),
hydroxypropylcellulose (HPC), methylcellulose (MC), crystalline
30 cellulose, polyvinylpyrrolidone (PVP), polyethylene glycol, gum arabic, dextran, polyvinyl alcohol (PVA), starch paste and the like.

Examples of the disintegrant include, but are not limited to, carboxymethylcellulose, calcium

carboxymethylcellulose, low-substituted hydroxypropylcellulose, crosslinking polyvinylpyrrolidone, carmellose sodium, croscarmellose sodium, sodium carboxymethyl starch, cation exchange resin, partially pregelatinized starch, corn starch
5 and the like.

Examples of the thickener include, but are not limited to, natural rubbers, cellulose derivative, acrylic acid polymer and the like.

Examples of the preservative include, but are not
10 limited to, p-hydroxybenzoic acid esters, chlorobutanol, benzyl alcohol, phenethyl alcohol, dehydroacetic acid, sorbic acid and the like.

Examples of the antioxidant include, but are not limited to, sulfite, ascorbic acid and their alkali metal salts,
15 alkaline earth metal salts and the like.

Examples of the coloring agent include, but are not limited to, synthetic coloring agents applicable to pharmaceutical products (e.g., sunset yellow etc. and aluminum lake thereof and the like), yellow ferric oxide, red ferric
20 oxide, riboflavin, riboflavin organic acid esters (e.g., riboflavin butyric acid ester), phosphoric acid riboflavin or alkali metal salt thereof, alkaline earth metal salt, phenol phthalein, titanium oxide and the like. As the light shielding agent, titanium oxide and the like can be mentioned.

25 Examples of the sweetening agent include, but are not limited to, saccharin sodium, dipotassium glycyrrhizinate, aspartame, stevia and the like.

The solid dosage form of the present invention can be formulated into a dosage form suitable for oral administration,
30 which is exemplified by, but not limited to, tablet, capsule and the like or parenteral administration such as suppository and the like, by processing the above-mentioned active ingredient and a suitable carrier according to a method known *per se*.

Tablets can be coated by a method known per se for the purpose of masking a smell or taste, stabilizing components, maintaining efficacy and the like. The coating can be largely divided into sugar coating and film coating (including enteric
5 coating and the like) according to its kind.

As a coating agent for sugar coating, sucrose is generally used. To enhance the binding property of a sugar coating layer and increase the mechanical strength, gelatin, gum arabic, methylcellulose, carboxymethylcellulose, sodium
10 carboxymethylcellulose, sodium starchglycolate, crystalline cellulose, polyvinylpyrrolidone, polyvinyl alcohol, sodium alginate and the like can be added. Furthermore, as an excipient or anti-tack agent, talc, precipitated calcium carbonate, kaolin and the like are used, and, for masking or
15 shading of color, a masking agent such as titanium oxide and the like are used.

As the film coating agent, for example, hydroxypropylmethylcellulose, ethylcellulose, hydroxypropylcellulose, tween80, and dyes such as titanium
20 oxide, ferric oxide (e.g., red ferric oxide, yellow ferric oxide) and the like are used. Moreover, photostability and the like can be improved by adding a masking agent and the like. These film coating formulations may contain, where necessary, talc and other excipients applicable to pharmaceutical
25 products. As the film coating agent, a base agent aiming at enteric coating and controlled release may be used besides those used for masking a taste, enhancing photostability or improving appearance. As a base agent for the film coating, hydroxypropylcellulose (HPC), hydroxypropylmethylcellulose
30 (HPMC), polyvinylpyrrolidone (PVP), ethylcellulose, polyvinyl acetal diethylamino acetate, cellulose acetate phthalate, methacrylic acid copolymers (e.g., methyl methacrylate-methacryl acid copolymers (Eudragit L100 or S100, manufactured by Rohm), methacrylic acid-ethyl acrylate copolymers (Eudragit

L100-55, L30D-55), methacrylic acid-methyl acrylate-methyl methacrylate copolymers (Eudragit FS30D, manufactured by Rohm)), hydroxypropylmethylcellulose phthalate (HP-55, HP-50, manufactured by Shin-Etsu Chemical Co., Ltd.),
5 carboxymethylethylcellulose (CMEC, manufactured by Freund Corporation), hydroxypropylcellulose acetate succinate (HPMCAS, manufactured by Shin-Etsu Chemical Co., Ltd.), polyvinyl acetate phthalate, shellac and the like can be used. They may be used alone, or at least two or more kinds of polymers may be
10 applied in combination, or at least two or more kinds of polymers may be applied successively.

Of these, as a coating material for controlling the release of the active ingredient in a pH-dependent manner, hydroxypropylmethylcellulose phthalates (HP-55, HP-50,
15 manufactured by Shin-Etsu Chemical Co., Ltd.), cellulose acetate phthalate, carboxymethylethylcellulose (CMEC, manufactured by Freund Corporation), methyl methacrylate-methacrylic acid copolymers (Eudragit L100 or S100, manufactured by Rohm), methacrylic acid-ethyl acrylate
20 copolymers (Eudragit L100-55, L30D-55), methacrylic acid-methyl acrylate-methyl methacrylate copolymer (Eudragit FS30D, manufactured by Rohm), hydroxypropylcellulose acetate succinate (HPMCAS, manufactured by Shin-Etsu Chemical Co., Ltd.), polyvinyl acetate phthalate, shellac and the like can be used.

25 The coating agents may be used alone or in combination as necessary. Where necessary, plasticizer, stabilizer and the like such as polyethylene glycol, dibutyl sebacate, diethyl phthalate, triacetine, triethyl citrate, copolyvidon and the like may be used for coating.

30 For coating, a method known per se, such as a pan coating method using a perforated coating system (e.g., Hicoater (trademark); Freund Corporation) and the like using a coating pan, a fluid bed coating method using a fluid bed granulation coating system (e.g., flow coater (trademark);

Freund Corporation) and the like, is employed.

Capsules can be produced by packing the above-mentioned active ingredient powder, or a powder mixture of the active ingredient and the above-mentioned carrier, or fine granules or
5 granules obtained by kneading or granulating the powder mixture and the like in a suitable capsule. The packed material (particularly fine particles or granules) may be film-coated as necessary, in a similar manner as that mentioned above with regard to the tablet.

10 As the capsule, one containing polyhydric alcohol such as glycerol, propylene glycol and the like or saccharide such as mannitol, sorbit and the like as a plasticizer in gelatin, which is molded suitably can be mentioned. Where necessary, the capsule may further contain a coloring agent and a
15 preservative similar to those mentioned above.

The treatment method of the present invention may be applied to a capsule filled with the packing material such as an active ingredient and the like. Alternatively, an empty capsule may be subjected to the treatment method of the present
20 invention, printed and filled with a packing material to give a finished preparation.

The treatment method of the present invention can also be applied not only to the above-mentioned solid dosage form but also any solid composition desired to carry a print on its
25 surface such as a food (e.g., sugar coated chocolate, gum, supplement and the like) and the like, particularly a solid composition requiring or desirably subjected to a treatment for improving the slip property and gloss.

The treatment method of the present invention is
30 characterized by a treatment of a surface of the solid dosage form with a polyethylene glycol-containing aqueous solution before printing. As used herein, by the "treatment" is meant "to apply" and refers to bringing a polyethylene glycol-containing aqueous solution into contact with the surface of a

solid dosage form after treatment, such that polyethylene glycol remains on the surface.

Polyethylene glycol to be used in the present invention is not particularly limited as long as it is not subject to any
5 limitation due to other reasons (e.g., range acceptable as a pharmaceutical additive when the solid dosage form is a pharmaceutical preparation). In consideration of the object of the present invention to improve durability of a print, however, polyethylene glycol is desirably present as a solid at
10 a temperature of the environment (e.g., 0 to 40°C, 10 to 30°C, 15 to 25°C) where the solid dosage form is preserved. For example, one having an average molecular weight of about not less than 1,000, more preferably about 3,000 to about 9,000, can be mentioned. In addition, two or more kinds of
15 polyethylene glycol having different average molecular weights may be used in a mixture.

The average molecular weight of polyethylene glycol is measured by a method according to the measurement method of the average molecular weight of macrogol 4000 in the Japan
20 Pharmacopoeia fourteenth Edition (hereinafter sometimes to be abbreviated simply as the Japan Pharmacopoeia).

The concentration of polyethylene glycol in the polyethylene glycol-containing aqueous solution is not particularly limited as long as it ensures that polyethylene
25 glycol remains on the surface of a solid dosage form after treatment in an amount sufficient to improve the abrasion resistance of a print to be produced on said surface. For example, it is about 1 to about 20 wt%, preferably about 5 to about 15 wt%.

30 The polyethylene glycol-containing aqueous solution can contain a component other than polyethylene glycol within the range free of a bad influence on the property of a print to be produced on the surface of a solid dosage form. As used herein, by the "property of a print" is meant properties

including quantitative and qualitative characteristics during printing, such as abrasion resistance after printing, incidence of incomplete print, printing stain and the like (= rate of printing failure) and level of the printing failure. For
5 example, when the treatment method of the present invention is applied to a plain tablet, the polyethylene glycol-containing aqueous solution contains a film coating agent since the solution also functions as a film coating liquid, as mentioned above. As the film coating agent, for example, those capable
10 of being dispersed in a water-soluble or aqueous solution can be mentioned, from the above-mentioned film coating agents.

In addition, the polyethylene glycol-containing aqueous solution can further contain a preparation additive as necessary, such as stabilizer, lubricant, preservative,
15 antioxidant, coloring agent, sweetening agent and the like. As the stabilizer, for example, tartaric acid, citric acid, succinic acid, fumaric acid, maleic acid and the like can be mentioned. As the lubricant, for example, talc, titanium oxide, magnesium stearate, calcium stearate, light anhydrous
20 silicic acid and the like can be mentioned. As the preservative, for example, p-hydroxybenzoic acid esters, chlorobutanol, benzyl alcohol, phenethyl alcohol, dehydroacetic acid, sorbic acid and the like can be mentioned. As the antioxidant, for example, sulfite, ascorbate and the like can
25 be mentioned. As the coloring agent, for example, water-soluble food tar colors (e.g., food dyes such as Food Red No. 2 and No. 3, Food Yellow No. 4 and No. 5, Food Blue No. 1 and No. 2 and the like), water insoluble lake colors (e.g., aluminum salts of the aforementioned water-soluble food tar colors),
30 natural colors (e.g., β -carotene, chlorophyll, ferric oxide) and the like can be mentioned. As the sweetening agent, for example, sodium saccharin, dipotassium glycyrrhizinate, aspartame, stevia and the like can be mentioned.

As mentioned above, the film coating liquid can contain

a plasticizer to control the softening temperature of the coating agent. When the polyethylene glycol-containing aqueous solution is a film coating liquid, polyethylene glycol itself can function as a plasticizer. A polyethylene glycol-
5 containing aqueous solution having a concentration necessary for improving the abrasion resistance of a print to be produced on the surface of a solid dosage form is sufficient to function as a plasticizer. When desired, other plasticizers, such as acetyltributyl citrate, acetyltriethyl citrate, castor oil,
10 diacetylation monoglyceride, dibutyl sebacate, diethyl phthalate, glycerol, mono- or di-acetylation monoglyceride, propyleneglycol, triacetine, triethyl citrate and the like may be further added.

When the polyethylene glycol-containing aqueous solution
15 contains a component other than polyethylene glycol, the proportion of polyethylene glycol in the whole components (excluding water) is about 1 to about 30 wt%, preferably about 10 to about 20 wt%.

For a treatment of the surface of a solid dosage form
20 with a polyethylene glycol-containing aqueous solution, various coating methods generally used in the field of preparations can be employed. Preferably, spray coating is applied using a coating pan, a fluid bed coating system and the like.

In the case of sugar-coated tablets, for example, after
25 completion of each step of sugar coating (i.e., waterproof coating, under coating, sub-coating, coloring, finishing), tablets are transferred to a cloth polishing pan, a predetermined amount of a polyethylene glycol-containing aqueous solution is sprayed or poured thereon while rotating
30 the pan, or a polyethylene glycol-containing aqueous solution is sprayed or poured thereon once to several times while rotating the pan until it reaches a predetermined coating weight.

In the case of film-coated tablets, for example, a

polyethylene glycol-containing aqueous solution is sprayed with a compressed air from a spray nozzle in the coating pan used for the film coating while rotating the pan, and the surface of the tablets is dried by heated air supplied. Alternatively, in
5 the fluid bed coating system used for the film coating, a polyethylene glycol-containing aqueous solution is sprayed from a spray nozzle while floating or fluidizing the tablets with an air flow and the surface of the tablets is dried with the air flow. The polyethylene glycol-containing aqueous solution is
10 sprayed in a predetermined amount, or the above-mentioned operation is repeated until a predetermined coat weight is achieved.

In the case of plain tablets, namely, when a polyethylene glycol-containing aqueous solution also functions
15 as a film coating liquid, a method employed for conventional film coating can be used directly. For example, a method similar to that of the above-mentioned film-coated tablets can be mentioned.

In the case of capsule, too, a method employed for
20 conventional film coating can be used similarly. When this treatment is applied after filling packing materials such as an active ingredient and the like, powder of the packing materials attached to the surface of the capsule during the filling is preferably removed with a conventional capsule polishing
25 machine before the treatment.

The weight of the coating film formed by the treatment method of the present invention is not particularly limited as long as it ensures that polyethylene glycol remains on the surface of a solid dosage form after treatment in an amount
30 sufficient to improve the abrasion resistance of a print to be produced on said surface. Preferably, it is appropriately selected from the range that makes the weight ratio of the amount of polyethylene glycol to be added by this treatment to the finished preparation fall within the range of about 0.01 to

about 1.0%, more preferably about 0.05 to about 0.7%.

The treatment method of the present invention can not only improve the abrasion resistance of a print to be produced on the surface of a solid dosage form, but also reduce the
5 frequency of printing failure (i.e., printing failure rate) during printing such as incomplete print, printing stain and the like, and advantageously further improve the printing performance as a whole.

Accordingly, the present invention also relates to a
10 production method of a solid dosage form having a print on its surface, which comprises treating the surface of the solid dosage form with a polyethylene glycol-containing aqueous solution and then printing on said surface. The treatment with a polyethylene glycol-containing aqueous solution can be
15 applied as mentioned above.

For printing, a method conventionally used in the art can be employed. As a solid dosage form delivery mechanism of a printing machine, any type can be used, including a slot type, a drum type, a link type and the like, and an appropriate
20 type can be selected according to the manufacturing scale and the like. While the printing method is not particularly limited, either, a photogravure offset printing method is often used. To be specific, a photogravure roll engraved with an identification code, a symbol and the like during a
25 photomechanical process is rotated in an ink tank to attach the ink, and redundant ink is scraped off with a blade (thin-bladed knife). The ink remaining in the engraving (concave) is transferred onto a rubber offset roll, and then transferred onto the solid dosage form in a printing section to complete
30 the printing. As the tablet (capsule) printing machine, commercially available ones from Markem Corporation, Hartnett, Matsuoka Machinery Works Co., Ltd, Qualicaps Co., Ltd. and the like can be used.

While the ink to be used for printing is not

particularly limited as long as it is harmless, it is desirably quick-drying, and has high abrasion resistance after drying. As the dye, titanium oxide, carbon black, iron oxide, tar dyes (e.g., acidic colors such as Red No. 2, Red No. 3, Red No. 102, 5 Red No. 104-(1), Red No. 105-(1), Red No. 106, Yellow No. 4, Yellow No. 5, Green No. 5, Blue No. 1, Blue No. 2 and the like) and the like are generally used. As the base agent, moreover, shellac and the like are used and, as the solvent, ethanol, n-butanol, isopropanol and the like are used.

10 The solid dosage form with a print on its surface, which is produced by the above-mentioned method, has novel and useful characteristic in that it shows remarkably improved abrasion resistance of prints as compared to conventional preparations obtained by applying, before printing, a polishing treatment 15 with a wax solution using an organic solvent or a powder wax or a wax-like substance. Accordingly, the present invention also provides a solid dosage form obtained by the above-mentioned method, which has a print on its surface.

The solid dosage form of the present invention can be 20 conferred a desirable characteristic of superior abrasion resistance of a print produced on its surface, due to the presence of a coating film containing polyethylene glycol on the surface of the solid dosage form. The "coating film" does not need to completely cover the surface of a solid dosage 25 form, as long as polyethylene glycol is substantially uniformly present at least on the area to be printed on. For example, the "coating film" may be in the state where a number of miniature films attach to the surface of a solid dosage form. As used herein, by "substantially uniform" is meant being 30 uniform to a degree sufficient to improve the abrasion resistance of the print. Therefore, the solid dosage form of the present invention is not restricted to the above-mentioned method, as long as it has the above-mentioned surface structure and superior abrasion resistance of the print, and may be

produced by any method.

Preferably, the solid dosage form of the present invention does not contain bees wax and carnauba wax in the coating film containing polyethylene glycol.

5 The solid dosage form of the present invention can be administered to the subject in the same manner as in conventional solid dosage forms.

The present invention is explained in detail in the following by referring to Examples, which are mere examples
10 and do not limit the scope of the present invention in any way.

Example 1

Reference Example Production of film-coated tablet

15 Formulation (unit: mg)

plain tablet

(containing 4 mg of active ingredient)	130.0
--	-------

hydroxypropylmethylcellulose

(TC-5; trademark)	3.74 (74.8%)
-------------------	--------------

²⁰ copolyvidon	0.75 (15.0%)
---------------------------	--------------

titanium oxide	0.5 (10.0%)
----------------	-------------

<u>yellow ferric oxide</u>	0.01 (0.2%)
----------------------------	-------------

total	135.0
-------	-------

25 Plain tablets were placed in a coating machine (Driacoater (Powrex Corporation) or Hicoater (Freund Corporation)), a film coating liquid containing TC-5, copolyvidon, titanium oxide and yellow ferric oxide at the above-mentioned weight ratios was sprayed with a spray nozzle
30 while rotating the pan, and the tablets were dried by heated air supplied. This operation was repeated until the above-mentioned coating weight was achieved.

Example 2

Pre-printing treatment with polyethylene glycol-containing aqueous solution formulation (unit: mg)

	Prepar. Ex. 1	Prepar. Ex. 2	Comp. Ex.
5 film-coated tablet			
(Reference Example)	135.0	135.0	135.0
MACROGOL 4000			
(the Japan Pharmacopoeia)	0.1		
MACROGOL 6000			
10 (the Japan Pharmacopoeia)		0.1	
water	(0.9)	(0.9)	
carnauba wax			0.008
sorbitan mono-oleate			0.04
n-hexane			(0.9625)

15

The film-coated tablets (6,000 tablets, 810 g) obtained in the above-mentioned Reference Example were placed in a Hicoater (Freund Corporation), and a 10 wt% aqueous solution of MACROGOL 4000 (the Japan Pharmacopoeia; molecular weight 2,600-
 20 3,800) (Preparation Example 1) or MACROGOL 6000 (the Japan Pharmacopoeia; molecular weight 7,300-9,300) (Preparation Example 2) in total 6.0 g, or a 0.79 wt% carnauba wax n-hexane solution (Comparative Example) in total 6.063 g was sprayed with a spray nozzle while rotating the pan to give respective
 25 tablets having the above-mentioned formulations.

The above-mentioned respective tablets were printed on by a conventional method using an organic solvent type ink (manufactured by Colorcon. Inc.) with a tablet printing machine (Matsuoka Machinery Works Co., Ltd).

30

Example 3

Experimental Example Test of print abrasion resistance of and printing failure rate

The three kinds of tablets (500 tablets each) obtained in the above-mentioned Example 2 were visually observed to examine printing failure, and 100 tablets each were placed in 3K glass bottles, which were shaken at amplitude 40 mm, shaking speed 250 times/minute in a reciprocal shaker SR-IIw (Nihon Medical and Chemical instruments Co., Ltd.) to observe the level of abrasion of the print over time. The results are shown in Table 1.

10

Table 1

		Comp. Ex.	Prep. Ex. 1	Prep. Ex. 2
appearance	number of test tablets	500	500	500
Class D (%) ¹⁾		0	0	0
Class C (%)		0	0	0
Class B (%)	incomplete print	2.0	0	0
	printing stain	1.4	1.2	0.8
	total	3.4	1.2	0.8
abrasion property ²⁾	10 min	print is scratchy, whole tablet is stained (+)	no change (±)	no change (±)
	30 min	print is scratchy, whole tablet is stained (++)	print is scratchy, whole tablet is stained (+)	no change (±)
	60 min	print is scratchy, whole tablet is stained (+++)	print is scratchy, whole tablet is stained, cloudy bottle (++)	print is scratchy, whole tablet is stained, cloudy bottle (++)

1) Class of appearance

Class B: readable print though partly missing, or printing stain of not more than 1 mm in length

5

Class C: partly unreadable print, or printing stain of more than 1 mm in length

Class D: unreadable print

10

2) Abrasion property

(±): No change from the start of shaking

15

(+): readable print though with slight change in printing state (scratching, stain and the like)

(++): clear change in printing state and partly unreadable print

20

(+++): marked change in printing state and mostly unreadable print

As is clear from Table 1, a pretreatment with a polyethylene glycol-containing aqueous solution resulted in remarkably improved abrasion resistance of the print as compared to the use of carnauba wax. Moreover, the printing failure rate showed a tendency toward lower levels. More superior results were obtained in both the abrasion resistance and printing failure rate by the use of MACROGOL 6000.

30

Industrial Applicability

According to the treatment method of the present invention, printability and abrasion resistance of a print to

be produced on a surface of the solid dosage form can be improved, and as a result, identification function of the solid dosage form can be maintained for a long time and good appearance is not impaired, and a solid dosage form with a high
5 commercial value can be provided.

The method for treating a solid dosage form of the present invention provides an effect of remarkably improved printability and abrasion resistance of the solid dosage form by treating, before printing, the surface of the solid dosage
10 form with a polyethylene glycol-containing aqueous solution.

While some of the embodiments of the present invention have been described in detail in the above, it is, however, possible for those of ordinary skill in the art to make various modifications and changes to the particular embodiments shown
15 without substantially departing from the teaching and advantages of the present invention. Such modifications and changes are encompassed in the spirit and scope of the present invention as set forth in the appended claims.

Those described in a singular form in the present
20 specification may be understood in a plural form, as long as they are not associated with clear inconsistencies with the context and the present invention.

All references cited herein, including patents and patent applications, are hereby incorporated in full by
25 reference, to the extent that they have been disclosed herein.

This application is based on a patent application No. 2003-401691 filed in Japan, the contents of which are incorporated in full herein by this reference.